

Flowshield LXP



A solvent free, flexible, polyurethane floor coating system that withstands a demanding industrial environment.





Flexible Application:

Can be installed on a variety of substrates including concrete, wood and steel



Crack Bridging:

30% elongation providing crack bridging properties



Wear Resistant:

Excellent abrasion, impact and wear resistance in high traffic areas



Chemical Resistance:

Protects against a range of acids, alkalis, solvents, alcohol and fuel

Technical Information ¹				
REACTION TO FIRE				
B _A -s1	EN 135	01-1		
SLIP RESISTANCE ²				
Dry > 40	EN 130	36-4		
TEMPERATURE RESISTANC	E			
Tolerant up to +60°C				
WATER PERMEABILITY				
Karsten test - Nil (Impermed	ıble)			
SURFACE HARDNESS				
65 (Shore'a scale)	ASTM D	2240		
WEAR RESISTANCE				
RWA1	EN 138	92-5		
FLEXURAL STRENGTH				
> 35 N/ mm ²	EN 13892-2			
TENSILE STRENGTH				
> 10 N/ mm ²	BS 6319			
IMPACT RESISTANCE				
IR13	EN ISO	EN ISO 6272-1		
BOND STRENGTH				
≥ 2,0 MPa	EN 154	EN 1542		
RELATIVE ELONGATION AT	BREAK			
60%	BS 6319	BS 6319		
SPEED OF CURE	+10°C	+20°C	+30°C	
Light Traffic	36 hrs	24 hrs	12 hrs	
Full traffic	72 hrs	48 hrs	24 hrs	

Standard colour chart

Full chemical cure



12 days

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local CPG Europe office.

Model Specification

System:	Flowshield LXP
Finish:	Gloss
Thickness:	0,7-3,0 mm
Colour	According to the catalog
Producer:	CPG Europe
Supplier:	Tremco CPG Poland Sp. z o.o.
Telephone:	+48 22 879 89 07

Installation Service

The installation should be carried out by a Flowcrete approved contractors with a documented quality assurance scheme. Obtain details of our approved contractors by contacting CPG Eastern Europe or enquiring via our website at www.flowcrete.com.pl.

Products Included in this System³

Primer	
Concrete:	Protop 1000 or Deckshield SF
Steel:	Peran Primer W
Wood:	Flowprime LXP
Asphalt concrete:	Not required
Main layer:	Flowshield LXP ⁴
Matt finish (optionally):	Flowseal PU Satin/Matt/Matt (Ultra)

³ If other resins are used contact CPG Eastern Europe for further details.

Detailed application instructions are available upon request.


Substrate Requirements

Concrete or screed substrate should be class min. C20/25, a minimum bond strength of 1,5 MPa (pulloff test), surface even, clean, free from laitance, dust and other contamination. All damages in the substrate should be repaired prior to applying the flooring. The substrate should be dry up to 75% RH as per BS 8204 (5% humidity measured by the Tramex method) and free from rising damp and ground water pressure. In case of higher humidity, one should use Hydraseal DPM as primer. Details to be found in the Flowcrete Resin Flooring Substrate Requirements.

Aftercare - Cleaning and Maintenance

Clean regularly manually or using a machine in conjunction with a mildly alkaline detergent. Flowcrete Flooring Cleaning Instruction available upon request.

System Design



Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless, impermeable surface with perfect adhesion to the substrate reduce the need for repairs and maintenance.

Complies with LEED EQ Credit 4.2. requirements: VOC content < 10 g/l.

Technical information, recommendations and instructions concerning the product use, storage and maintenance included in this System Data Sheet are based on Tremco CPG Poland Sp. z o.o. (further related as "CPG Polska") knowledge and experience, reflecting the best acknowledged way of using the material for a given moment. Taking into consideration other factors that are beyond the producer's control, including differences in quality of substrates, tools and other complementary materials, weather conditions, proper installation and also cleaning and maintenance, CPG Polska cannot take responsibility in case of failure to conform with information and instructions included in this System Data Sheet or, respectively, written recommendations from authorized CPG Polska representatives. One should always conform with up-to-date names and building principles, and also safely, typiquen and health protection rules according to the information included in Material Safety Data Sheets and also on the products packaging. This System Data Sheet replaces all previous versions. In order to receive up-to-date System Data Sheets contact CPG Polska.



ul. Marywilska 34, 03-228 Warsaw, Poland tel.: +48 22 879 8907 email: poland@cpg-europe.com



⁴ Flowshield LXP and Peran SL-C are used for a system thickness ≥ 2.0 mm.