

## Mondéco ESD Earth (8 mm)

Anti-static, hygienic epoxy terrazzo floor finish. To provide a hard wearing, decorative, seamless, anti-static floor.



### Attractive:

Extensive and flexible design to deliver the wow-factor underfoot.



### Seamless Finish:

Except for underlying slab joints and edging detail trim.



### Highly Chemical Resistant:

Protects against a variety of aggressive acids, solvents and caustics.



### Easy to Clean:

Easy to clean and maintain, seamless surface with excellent life span.



### Temperature Resistant:


Tolerant of sustained temperatures up to 60°C.




Provence Blue



Coconut




Dusty Grey



Chilli Pepper



Agate Grey



Oyster White


The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

## Technical Profile\*

ELECTRICAL RESISTANCE				
EN IEC 61340-5-1	$5 \times 10^4 - 1 \times 10^9 \Omega$			
REACTION TO FIRE				
EN 13501-1	B <sub>fl</sub> -s1			
WEAR RESISTANCE				
EN 13892-4	Max. wear depth <50 µm			
BOND STRENGTH				
EN 13892-8	>2.0 N/mm <sup>2</sup>			
IMPACT RESISTANCE				
EN ISO 6272	16 Nm			
BS 8204-1	Cat: A (<0.5mm)			
COMPRESSIVE STRENGTH				
EN 13892-2	>55 N/mm <sup>2</sup>			
WATER PERMEABILITY				
Karsten test	Nil (Impermeable)			
SLIP RESISTANCE*** (in accordance with HSE and UKSRG guidelines)				
Method described in BS 7976-2 (typical values for 4-S rubber slider)	Dry >40 low slip potential			
BS 8204-6/FERFA				
Type 8				
SPEED OF CURE**		10°C	20°C	30°C
Light Traffic	24 hrs	16 hrs	10 hrs	
Full Traffic	72 hrs	48 hrs	36 hrs	
Full Chemical Cure	12 days	7 days	7 days	

\* The figures that follow are typical properties achieved in laboratory tests at 20°C and at 50% Relative Humidity.

\*\*\* The slipperiness of flooring materials can change significantly, due to the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/or surface contaminants (wet or dry). Textured systems are recommended to meet slip resistance value requirements for wet conditions and/or surface contaminants (wet or dry) - please contact our Technical Advisors for further details and specifications.



\*\*Cure times at temperatures between 0–30°C can be achieved by altering the quantity of catalyst used. For applications falling outside of this temperature range, please contact your local Flowcrete Technical Department.

## Model Specification

<b>System</b>	Mondéco ESD Earth
<b>Finish</b>	Satin / Matte

Preparatory work and application in accordance with manufacturer's instructions.

## Products Included In This System

<b>Primer</b>	Flowprime @ 0.25 kg/m <sup>2</sup> Conductive Grid of 10 mm wide copper tape.
<b>Primer</b>	Flowprime @ 0.25 kg/m <sup>2</sup> with Conductive Scatter @ ~2 kg/m <sup>2</sup>
<b>Topping</b>	Mondéco ESD Earth (avge density 2.1 kg/l) @ 21 kg/m <sup>2</sup> (Applied at 10 mm, ground down to 8 mm)
<b>Grout</b>	Mondéco/Mirrazzo Grout @ up to 0.2 kg/m <sup>2</sup> Applied in 1 or 2 layers
<b>Sealers (1<sup>st</sup> Layer)</b>	ESD PU Base Coat @ 0.05 kg/m <sup>2</sup>
<b>Sealers (2<sup>nd</sup> Layer)</b>	ESD PU Top Coat @ 0.05 kg/m <sup>2</sup>

Detailed application instructions are available upon request.

## Note

Mondéco/Mirrazzo is not totally colour fast and may change colour over time (exhibits a yellowing effect). Colour change depends on the UV light and heat levels present and hence the rate of change cannot be predicted. This is more noticeable in very light colours but does not compromise the product's flexibility or chemical resistance characteristics. We have endeavoured to adopt colours within our standard range which minimise this change. Separate each adjacent application bay (a day's lay) by a trim and ensure that single batch components are used within each

bay. Intensively coloured products (e.g. hair colourants, medical disinfectants etc.) and plasticizer migration (e.g. from rubber tyres) can lead to irreversible discolouration in the surface. Please contact our Technical Services Department for further advice.

## Substrate Requirements

Concrete or screed substrate should be a minimum of 25N/mm<sup>2</sup>, free from laitance, dust and other contamination. The substrate should be dry to 75% RH as per BS8203 and free from rising damp and ground water pressure. If no damp proof membrane is present Hydraseal DPM can be incorporated directly beneath the Mondéco system.

## Installation Service

The installation must be carried out by a Flowcrete approved contractor with a documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via our website [www.flowcrete.co.uk](http://www.flowcrete.co.uk).

## Aftercare, Cleaning & Maintenance

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a neutral detergent / floor maintainer and dry burnish. Maintain the surface appearance with a suitable high solids metallised floor polish as required (dependant on levels of traffic).

## Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning.

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request. Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

System Datasheet written for Flowcrete UK Ltd. Please consult Technical Team in your own country region for specific details. [12/02/19, 01 UK]