

## Peran STB Classic for Wet Areas (5 mm)

A decorative resin floor with colour stable quartz granules in a clear low emission resin binder.



### Attractive:

Decorative floor finish that delivers the wow-factor underfoot.



### Wear Resistant:

Excellent general wear, tear, impact and chemical resistance underfoot.



### Slip Resistant:

Slip resistant textured finish, ideal for areas that are often wet underfoot.

### Commercial



Beige 101    Biscuit 102    Black 901    Dark Grey 703



Grass Green 601    Light Grey 701    Mid Blue 501    Mid Grey 702

### Industrial



Blue 502    Cream 103    Green 602    Grey 704



Red 301    Yellow 104

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

CE	08
	EN 13813


Low emission systems with M1 Certification are available. For more information, contact your local Flowcrete office.

## Technical Profile\*

FIRE RESISTANCE				
EN 13501-1	B <sub>f</sub> -s1			
WEAR RESISTANCE				
EN 13892-5	Abrasion quantity 1 cm <sup>3</sup>			
TEMPERATURE RESISTANCE				
Tolerant up to 70°C (intermittent) or 50°C (sustained)				
IMPACT RESISTANCE				
EN ISO 6272	15 Nm			
BOND STRENGTH				
EN 13892-8	>2.5 N/mm <sup>2</sup>			
COMPRESSIVE STRENGTH				
EN 13892-2	>40 N/mm <sup>2</sup>			
WATER PERMEABILITY				
Karsten Test	Nil (Impermeable)			
VAPOUR PERMEABILITY				
ASTM E96:90	1.36 g / m <sup>2</sup> / mm / 24 hrs			
SLIP RESISTANCE** (in accordance with HSE and UKSRG guidelines)				
BS 7976-2 (typical values for 4-S rubber slider)	Dry >40 low slip potential Wet >40 low slip potential			
BS 8204-6 / FeRFA				
Type 6				
SPEED OF CURE		10°C	20°C	30°C
Light Traffic		36 hrs	24 hrs	16 hrs
Full Traffic		72 hrs	48 hrs	48 hrs
Full Cure		12 days	7 days	7 days

\*These figures are typical properties achieved in laboratory tests at 20°C and at 50% Relative Humidity.

\*\*The slipperiness of flooring materials can change significantly, due to the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/ or surface contaminants (wet or dry). Textured systems are recommended to meet slip resistance value requirements for wet conditions and/ or surface contaminants (wet or dry) - please contact our Technical Advisors for further details and specifications.



For any other information please contact your local Flowcrete Technical Department.

## Model Specification

<b>System</b>	Peran STB Classic for Wet Areas
<b>Finish</b>	Matte

Preparatory work and application in accordance with manufacturer's instructions.

## Products Included In This System

<b>Primer</b>	Peran STC @ 0.25 kg/m <sup>2</sup>
<b>Scatter</b>	Coloured Quartz Size 7/8 @ 0.50 kg/m <sup>2</sup>
<b>Topping</b>	Peran STC (as binder) @ 0.80 kg/m <sup>2</sup> mixed with Coloured Quartz Size 7/8 @ 6.60 kg/m <sup>2</sup>
<b>Sealer</b>	Peran TCW @ 0.80 kg/m <sup>2</sup>
<b>Scatter</b>	Coloured Quartz Size 8 @ 2.0 kg/m <sup>2</sup>
<b>Sealer</b>	Peran STC @ 0.4 to 0.6 kg/m <sup>2</sup> (in two or more coats dependant on the surface texture required) and Flowseal PU Matte @ 0.08 kg/m <sup>2</sup>

Detailed application instructions are available upon request.

## Substrate Requirements

Concrete or screed substrate should be a minimum of 25 N/mm<sup>2</sup>, free from laitance, dust and other contamination. The substrate should be dry to 75% RH as per BS8203 and free from rising damp and ground water pressure. If no damp proof membrane is present Hydraseal DPM can be incorporated directly beneath the Peran STB system.

## Installation Service

The installation should be carried out by a Flowcrete approved contractor with a documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via our website [www.flowcrete.co.uk](http://www.flowcrete.co.uk)

## Aftercare

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request.

## Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning.

Environmental and health considerations are controlled during manufacture and application of the products by Flowcrete staff and fully trained and experienced contractors.

## Note

No resin system is totally colour fast and may change colour over time (exhibits a yellowing effect). Colour change depends on the UV light and heat levels present and hence the rate of change cannot be predicted. This is more noticeable in very light colours but does not compromise the product's physical or chemical resistance characteristics. We have endeavoured to adopt colours within our standard range which minimise this change.

Intensively coloured products (e.g. hair colourants, medical disinfectants etc.) and plasticizer migration (e.g. from rubber tyres) can lead to irreversible discolouration in the surface. Please contact our Technical Services Department for further advice.

Flowcrete's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request. Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

System Datasheet written for Flowcrete UK Ltd. Please consult Technical Team in your own country region for specific details. [11/12/18, 01 UK]